


	Th-1101011	Character De austre au carte	T D
	Technical Specifications	Standard Requirements	Test Results
<u></u>	Water Absorption UNI EN ISO 10545-03	E≤0.5%	≤ 0.5%
<u></u>	Breaking Strength UNI EN ISO 10545-04	≥ 1300 N	≥ 1500 N
<u></u>	Modulus of Rupture UNI EN ISO 10545-04	> 35 N/mm²	≥ 37 N/mm²
<u> </u>	Shock Resistance UNI EN ISO 10545-05	Suggested Minimum: E > 0.55	Resistant
<b>(</b>	Resistance to Deep Abrasion UNI EN ISO 10545-06	Maximum: 175 mm³	N/A
<u>±</u> →	Thermal Linear Expansion UNI EN ISO 10545-08	As Reported	65 x 10 <sup>-5</sup> /°C <sup>-1</sup>
洙	Thermal Shock Resistance UNI EN ISO 10545-09	Required	Resistant
٥٥٥	Moisture Expansion UNI EN ISO 10545-10	As Reported	≤ 0.6 mm/m
*	Frost Resistance UNI EN ISO 10545-12	As Reported	Resistant
M	Chemical Resistance UNI EN ISO 10545-13	Domestic Chemical Products: GB Acids and Alkalis: As Reported	GB GLB
×	Stain Resistance UNI EN ISO 10545-14	Minimum: Class 3	Class 3
PEI	PEI Rating (Scratch Resistance) ASTM C 1027	As Reported	III
Š.	Dynamic Coefficient of Friction (DCOF) ANSI A137.1	For Level Interior Spaces Expected to be Walked Upon When wet: > 0.42	≥ 0.42
	Shade Variation	As Reported	V3
<b>↓</b>	Thickness	As Reported	12" x 24" - 8.5 mm 24" x 24" - 8.5 mm
Ш	Number of Screens	As Reported	12" x 24" - 16 24" x 24" - 8

# Grout joint required for rectified edge tile 1/2 broken joint not recommended



















The data refers to first choice material in the natural version.














# **FORMATS**

## LIGHT GREY







### **GREY**







GRAFITTI







ALL FORMATS AVAILABLE IN NATURAL FINISH

# LIGHT GREY (FLOOR)

# SOFT STONE

Soft Stone brings evelated minialism to living spaces with diagonal movements throughout its distribution. This collection's soft momentum creates sophisticated visual interest

effortlessly. Available in three neutral greys with an assortoment of tone shifts in each, Soft Stone lends itself to a variety of design possibilities.